

07783.0067.CPUS02  
Application No. 10/788,628

**AMENDMENT**

**In the Claims:**

1. (currently amended) A method for improving the adhesion properties and switching performance of an electrophoretic display wherein display cells are filled with an electrophoretic fluid comprising a solvent, which method comprises (a) applying an adhesive composition to a component of said electrophoretic display, or (b) sealing the filled display cells with a sealing composition, wherein said adhesive or sealing composition comprises

- (i) a polymer or oligomer having a dielectric constant higher than that of the solvent,
- (ii) a radically or photochemically graftable polymer, wherein the polymer or oligomer of (i) is grafted onto the graftable polymer of (ii).
- (iii) optionally a crosslinking agent, and
- (iv) a catalyst which is optionally present when the crosslinking agent is present.

2. (previously presented) The method of Claim 1 wherein said polymer or oligomer of (i) has a dielectric constant in the range of about 3.5-17 measured at 18-27°C and at 60Hz.

3. (previously presented) The method of Claim 2 wherein said polymer or oligomer of (i) has a dielectric constant in the range of about 6-15 measured at 18-27°C and at 60Hz.

4. (previously presented) The method of Claim 1 wherein said polymer or oligomer of (i) is a polyurethane, polyurea, polycarbonate, polyamide, polyester, polycaprolactone, polyvinyl alcohol, polyether, polyvinyl acetate derivative, polyvinyl fluoride, polyvinylidene fluoride, polyvinyl butyral, polyvinylpyrrolidone, poly(2-ethyl-2-oxazoline), high-acid-number acrylic or methacrylic polymer or copolymer, gum Arabic, alginate, lecithin or polymer derived from an amino acid.

5. (previously presented) The method of Claim 4 wherein said polymer or oligomer of (i) comprises a functional group for chain extension or crosslinking.

07783.0067.CPUS02  
Application No. 10/788,628

6. (previously presented) The method of Claim 4 wherein said polymer or oligomer of (i) is selected from the group consisting of polyurethanes, polyureas, polycarbonates, polyesters and polyamides.

7. (previously presented) The method of Claim 6 wherein said polymer or oligomer of (i) comprises a functional group selected from the group consisting of -OH, -SH, -NCO, -NCS, -NHR, -NRCONHR, -NRCSNHR, vinyl, epoxide and derivatives thereof, wherein R is hydrogen, alkyl, aryl, alkylaryl or arylalkyl.

8. (previously presented) The method of Claim 7 wherein said polymer or oligomer of (i) is a functionalized polyurethane.

9. (original) The method of Claim 8 wherein said functionalized polyurethane is hydroxyl terminated polyester polyurethane or polyether polyurethane, isocyanate terminated polyester polyurethane or polyether polyurethane or acrylate terminated polyester polyurethane or polyether polyurethane.

10. (original) The method of Claim 9 wherein said functionalized polyurethane is a hydroxyl terminated polyester polyurethane.

11. (cancelled)

12. (withdrawn) The method of Claim 1 wherein said radically or photochemically graftable polymer is a cellulose derivative or a polyvinyl alcohol derivative.

13. (withdrawn) The method of Claim 12 wherein said cellulose is cellulose acetate butyrate, cellulose acetate propionate, hydroxypropyl cellulose, hydroxybutyl cellulose, hydroxyethyl cellulose, methyl cellulose, carboxymethyl cellulose, or a copolymer thereof.

14. (withdrawn) The method of Claim 12 wherein said polyvinyl alcohol derivative is polyvinyl acetal, polyvinyl butyral, or a copolymer thereof.

15. (withdrawn) The method of Claim 1 wherein said radically or photochemically graftable polymer is cellulose acetate, cellulose acetate butyrate, cellulose acetate propionate, polyvinyl acetal or a copolymer thereof.

07783.0067.CPUS02  
Application No. 10/788,628

16. (withdrawn) The method of Claim 1 wherein said radically or photochemically graftable polymer is present in an amount of about 5% to about 30% by weight of the polymer or oligomer of (i) .

17. (withdrawn) The method of Claim 16 wherein said radically or photochemically graftable polymer is present in an amount of about 10% to about 20% by weight of the polymer or oligomer of (i).

18. (previously presented) The method of Claim 1 wherein said adhesive or sealing composition further comprises a photoinitiator.

19. (previously presented) The method of Claim 18 wherein said photoinitiator is benzophenone, isopropyl thioxanthone, 4(p-tolylthio)benzophenone, 2,2-dimethoxy-1,2-diphenylethane, 2-methyl-1-[4-(methylthio)phenyl]-2-morpholino-1-propanone, 2-benzyl-2-(dimethylamino)-1-[4-(4-morpholinyl)phenyl]-1-butanone or 1-hydroxycyclohexylphenylketone.

20. (previously presented) The method of Claim 18 wherein said photoinitiator is present in an amount of about 0.5% to about 5% by weight based on the total weight of the polymer or oligomer of (i) and the radically or photochemically graftable polymer.

21. (previously presented) The method of Claim 20 wherein said photoinitiator is present in an amount of about 1% to about 3% by weight based on the total weight of the polymer or oligomer of (i) and the radically or photochemically graftable polymer.

22. (original) The method of Claim 1 wherein said crosslinking agent is a multifunctional isocyanate.

23. (original) The method of Claim 22 wherein said multifunctional isocyanate is an aliphatic polyisocyanate.

24. (cancelled)

25. (cancelled)

07783.0067.CPUS02  
Application No. 10/788,628

26. (previously presented) The method of Claim 1 wherein said catalyst is selected from the group consisting of organotin catalysts, organozirconium catalysts and bismuth catalysts.

27. (original) The method of Claim 26 wherein said organotin catalyst is dibutyltin dilaurate.

28-38. (cancelled)

39. (original) The method of Claim 1 wherein said electrophoretic display is prepared using the microcup technology.

41-42. (cancelled)